

Technical Data Sheet

## HENSOTOP SB

Single component solvent-based top coat for HENSOTHERM® fire protection coating systems for indoor and outdoor use

### SUBSTRATES / PROPERTIES

Substrates: HENSOTHERM® fire protection coatings

- Solvent-based, 1-pack top coat based on acrylic resin
- Fast drying
- Halogen-free

### PRODUCT DATA

#### HENSOTOP SB

**Colour:** RAL, NCS, DB, Sikkens or samples available

**Gloss level:** Silky matt (<30 gloss units at 60°) / The gloss level varies depending on the colour shade.

**Packaging:** 5 kg, 10 kg and 25 kg tin pails / Standard colour shades also available in 2.5 kg tin pails

**Preparation:** Stir well before use!

**Thinning** with HENSOTHERM® V 45 max. 10% | **Cleaning** with HENSOTHERM® V 45

**Shelf life:** 12 months in unopened original pails at ambient temperatures in dry conditions

#### HENSOTOP SB / Reference values (theoretical values without losses)

<b>Specific gravity (g/ml)</b> 1.2	<b>Coverage rate (m<sup>2</sup>/kg)</b> I: approx 7   A: approx 4	<b>Volume solid (%)</b> 49
<b>Consumption rate (kg/m<sup>2</sup>)</b> I: 0.130–0.180   O: 0.260–0.300	<b>Wet film thickness (µm)</b> I: 130   O: 250	<b>Dry film thickness (µm)</b> I: 60–70   O: 80–100

I = Indoor use | O = Outdoor use

### APPLICATION INSTRUCTIONS

Recommendation at temperatures of approx +20 °C



Airless



Roller / Brush

<b>Nozzle size (inch)</b>	<b>0.009-0.013</b>	-
<b>Operation pressure (bar)</b>	<b>120-150</b>	-
<b>DFT* per layer (µm)</b>	<b>60-70</b>	<b>60-70</b>
<b>Thinning with thinner (%)</b>	<b>0-10</b>	<b>0</b>

\*DFT = Dry film thickness

<b>Drying time at 60 µm DFT</b>	<b>Ambient temperature +20 °C</b>
 Dust dry: Ready for overcoating: Dried through:	after approx 45 minutes after approx 24 hours after approx 48 hours

## APPLICATION INSTRUCTIONS

### Use / Application

HENSOTOP top coats offer the possibility of coloured design, protection against moisture and should be applied when the surfaces, during the usage, are exposed to environmental influences, regular cleaning and similar external influences. Do not apply the top coat before the HENSOTHERM® fire protection is fully dried! At the earliest after 24 hours and after a positive fingernail test.

- Material, substrate and ambient temperature > +10 °C
- Relative humidity < 80 %
- Application by brush, short pile velour or mohair paint roller or airless spraying.

### Note:

- If steel surfaces or wood components are regularly exposed to intense heat / high temperatures > +45 °C, do not use dark colours as a top coating.
- If HENSOTOP SB must be applied out of different batches, mix both materials (of the same colour shade) together before application.
- Colour shades containing metallic pigments may change by thinning with water or by application by brush or roller
- Due to thermal heating of the steel or wood components and possible blistering from residual solvent retention or on wood due to wood moisture, when using HENSOTHERM® 310 KS / HENSOTHERM® 370 KS as well as using the HENSOTHERM® 2 KS systems, do not use dark colours, such as the bold marked colour shades, as top coating whether for outdoor use or indoor use behind glass facades. We do not assume any warranty.



**Air and surface temperatures:** The temperature of the steel surface and the ambient temperature must remain between +15 °C up to +25 °C during the coating procedure. Not below +10 °C or above +35 °C! During the application and the drying, the surface temperature of the coated part must be at least +3 °C above the dew point of the ambient temperature and up to a maximum temperature of ≤ +35 °C!



**Relative humidity** max. 80 %

## COATING SYSTEMS

### Products

<b>Primer</b>	HENSOGRUND WB Green, HENSOGRUND 1K AK, HENSOGRUND 1966E, HENSOGRUND 2K, HENSOGRUND 2K PU, HENSOGRUND 2K EP
<b>Fire protection coating</b>	HENSOTHERM® 410 KS, HENSOTHERM® 421 KS, HENSOTHERM® 461 KS, HENSOTHERM® 471 KS, HENSOTHERM® 310 KS, HENSOTHERM® 370 KS
<b>Top coat</b>	HENSOTOP top coats are available in RAL or NCS colour shades and on request in individual colour shades.

## GROUPS OF COLOUR SHADES (RAL)

Standard	white, <b>7016</b> , 7035, 9002
Group I	1001, 1013, 1014, 1015, 1019, 1020 / 4009 / <b>5007, 5008, 5009</b> , 5018 / <b>6000, 6003, 6006</b> , 6011, <b>6012</b> , 6013, <b>6014, 6015</b> , 6019, <b>6020</b> , 6027, <b>6028</b> , 6033, 6034 / 7000, 7001, 7002, 7003, 7004, <b>7005, 7006, 7008, 7009, 7010, 7011, 7012, 7013, 7015, 7021, 7022</b> , 7023, <b>7024, 7026</b> , 7030, <b>7031</b> , 7032, 7033, 7034, 7036, 7037, 7038, <b>7039</b> , 7040, 7042, <b>7043</b> , 7044, 7045, 7046, 7047 / 8000, <b>8002, 8004, 8015, 8016, 8017, 8019, 8022, 8024, 8025, 8028</b> / 9001, 9003, <b>9004</b> , 9010, <b>9011</b> , 9016, <b>9017</b> , 9018
Group II	1000, <b>1011</b> , 1024 / <b>3007, 3009, 3011</b> , 3012, 3015 / <b>4005 / 5000, 5001, 5002, 5004, 5005</b> , 5012, 5014, 5015, <b>5019, 5021, 5023</b> , 5024 / <b>6004, 6008, 6016</b> , 6017, 6021, <b>6022, 6025</b> , 6032 / 8001, <b>8003, 8007, 8008, 8011, 8012, 8014 / 9005</b> , 9006, 9007, DB 701, DB 702, <b>DB 703</b>
Group III	1002, 1007, 1012, 1017, 1018, 1034 / <b>2001</b> , 2003, 2004, 2008, 2010, 2012 / <b>3000, 3001, 3002, 3005, 3013</b> , 3014, 3017, 3018, 3022, <b>3027, 3031 / 4001, 4002, 4003, 4006, 4007, 4008 / 5003, 5010, 5011, 5013, 5017, 5020, 5022 / 6001, 6002, 6005, 6007, 6009, 6010</b> , 6018, 6024, <b>6026, 6029 / 8023</b>
Group IV	1003, <b>1005</b> , 1006, 1016, 1027, 1033 / 2000, <b>2002</b> , 2009, 2011 / <b>3003, 3004, 3016 / 4004</b> , 4010
Group V	1004, 1021, 1023, 1028, 1032 / <b>3020, ca. 6037 / 7048 / DB 301, DB 310</b> , DB 501, DB 502, DB 503, <b>DB 510</b> , DB 601, DB 704, other DB colour shades on request

Special colour shades according Sikkens, NCS or samples available on request – minimum quantity 10 kg.

## PRECAUTIONS FOR SAFETY USE



Use HENSOTOP SB in accordance with all applicable local and national regulations.  
**Giscode: BS60**

The information provided herein reflects the current state of our technical testing and experience with the use of this product. However, the buyer/user is hereby not relieved of their duty, at their own responsibility, to properly examine our materials for their suitability for the intended use based on the respective site conditions. Legal claims for damages arising from the use of this product for purposes other than, or in a manner that differs from, the description contained herein without our prior written approval are precluded and may not be asserted against us. In light of the circumstance that we have no influence over site conditions and various factors that could influence the performance and use of our product, a guarantee of results or liability, regardless of legal grounds, cannot be derived from this information or from verbal consultation provided by one of our employees unless we may be accused of intent or gross negligence. Our General Terms and Conditions apply for all other purposes ([www.rudolf-hensel.de/gtc](http://www.rudolf-hensel.de/gtc)). The most recent version of our technical data sheet is valid and may be requested from the Rudolf Hensel GmbH or downloaded at [www.rudolf-hensel.de](http://www.rudolf-hensel.de).

© Rudolf Hensel GmbH 06/21

## **RUDOLF HENSEL GMBH**

Lack- und Farbenfabrik

Lauenburger Landstraße 11  
21039 Börnsen | Germany

Tel. +49 40 72 10 62-10  
Fax +49 40 72 10 62-52

E-Mail: [contact@rudolf-hensel.de](mailto:contact@rudolf-hensel.de)  
Internet: [www.rudolf-hensel.de](http://www.rudolf-hensel.de)

